

## TECHNICAL SPECIFICATIONS

Basis Weight	Thickness	Stiffness Taber 15°	
		MD (gramf x cm) (c)	CD (gramf x cm) (c)
g/m <sup>2</sup> (a)	µm (b)		
280	340	100	36
300	360	120	42
320	380	148	53
350	425	190	70
400	485	260	100
450	555	350	140
500	620	440	175
550	700	510	205

<b>Humidity (%)</b>	6-8
<b>Brightness ISO (Elrepho) (%)</b>	Top 80 ± 2
<b>Cobb 1'</b>	Top Side 35-65
<b>Bulk</b>	1.23 cm <sup>3</sup> /g (d)
<b>Delamination (ft*lb*10<sup>-3</sup>)</b>	MD ≥ 50 CD ≥ 50
<b>Gloss</b>	40-55

<b>*Tolerances</b>	a (±3%)
	b (-6%)
	c (-15%)
	d (±5%)

### Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

### The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products