

## TECHNICAL SPECIFICATIONS

| Basis Weight         | Thickness | Stiffness Taber 15° |                     |
|----------------------|-----------|---------------------|---------------------|
|                      |           | MD (gramf x cm) (c) | CD (gramf x cm) (c) |
| g/m <sup>2</sup> (a) | µm (b)    |                     |                     |
| 280                  | 340       | 88                  | 31                  |
| 300                  | 360       | 107                 | 37                  |
| 320                  | 380       | 134                 | 48                  |
| 350                  | 425       | 174                 | 64                  |
| 375                  | 457       | 208                 | 79                  |
| 385                  | 470       | 221                 | 84                  |
| 400                  | 485       | 241                 | 93                  |
| 420                  | 507       | 276                 | 107                 |
| 450                  | 540       | 328                 | 129                 |
| 500                  | 620       | 414                 | 164                 |
| 550                  | 685       | 480                 | 192                 |
| 600                  | 750       | 545                 | 220                 |

|   |                             |
|---|-----------------------------|
| <b>Humidity (%)</b>                         | 6-8                         |
| <b>Brightness ISO (Elrepho) (%)</b>         | Top 80 ± 2                  |
|   | Back 66-72                  |
| <b>Cobb 1'</b>                              | Top Side 35-65              |
| <b>Bulk</b>                                 | 1.23 cm <sup>3</sup> /g (d) |
| <b>Delamination (ft*lb*10<sup>-3</sup>)</b> | MD >= 50 CD >= 50           |
| <b>Gloss</b>                                | 40-55                       |

|                    |          |
|--------------------|----------|
| <b>*Tolerances</b> | a (±3%)  |
|                    | b (-6%)  |
|                    | c (-15%) |
|                    | d (±5%)  |

### Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

### The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products